

SECTION 071113 - BITUMINOUS DAMPPROOFING

PART 1 - GENERAL

1.1 RELATED DOCUMENTS

- A. Drawings and general provisions of the Contract, including General and Supplementary Conditions and Division 1 Specification Sections, apply to this Section.

1.2 SUMMARY

- A. This Section includes cold-applied, cut-back asphalt dampproofing applied to the following surfaces:
 - 1. Exterior face of inner wythe of exterior masonry cavity walls.
- B. Related Sections:
 - 1. Division 07 Section "Self-Adhering Sheet Waterproofing" for waterproofing.

1.3 SUBMITTALS

- A. Product Data: For each type of product indicated. Include recommendations for method of application, primer, number of coats, coverage or thickness, and protection course.

1.4 QUALITY ASSURANCE

- A. Source Limitations: Obtain primary dampproofing materials and primers through one source from a single manufacturer. Provide secondary materials recommended by manufacturer of primary materials.

1.5 PROJECT CONDITIONS

- A. Weather Limitations: Proceed with installation only when existing and forecasted weather conditions permit asphalt dampproofing to be performed according to manufacturers' written instructions.

PART 2 - PRODUCTS

2.1 MANUFACTURERS

- A. Manufacturers: Subject to compliance with requirements, provide products by one of the following:
 - 1. Cold-Applied, Cut-Back (Solvent-Based) Asphalt Dampproofing:
 - a. Gardner Asphalt Corporation.
 - b. Henry Company.
 - c. Karnak Corporation.
 - d. Koppers Industries, Inc.
 - e. Malarkey Roofing Company.

- f. Meadows, W. R., Inc.
- g. Sonneborn, Div. of ChemRex, Inc.
- h. Tamms Industries.

2.2 BITUMINOUS DAMPPROOFING

- A. Odor Elimination: For interior and concealed-in-wall uses other than exterior face of inner wythe of cavity walls, provide dampproofing material warranted by manufacturer to be substantially odor free after drying for 24 hours under normal conditions.
- B. Cold-Applied, Cut-Back (Solvent-Based) Asphalt Dampproofing:
 - 1. Brush and Spray Coats: ASTM D 4479, Type I.

2.3 MISCELLANEOUS MATERIALS

- A. Cut-Back Asphalt Primer: ASTM D 41.
- B. Emulsified-Asphalt Primer: ASTM D 1227, Type III, Class 1, except diluted with water as recommended by manufacturer.

PART 3 - EXECUTION

3.1 EXAMINATION

- A. Examine substrates, with Applicator present, for compliance with requirements for surface smoothness and other conditions affecting performance of work.
 - 1. Begin dampproofing application only after substrate construction and penetrating work have been completed and unsatisfactory conditions have been corrected.

3.2 PREPARATION

- A. Protection of Other Work: Mask or otherwise protect adjoining exposed surfaces from being stained, spotted, or coated with dampproofing. Prevent dampproofing materials from entering and clogging weep holes and drains.
- B. Clean substrates of projections and substances detrimental to work; fill voids, seal joints, and apply bond breakers if any, as recommended by prime material manufacturer.

3.3 APPLICATION, GENERAL

- A. Comply with manufacturer's written recommendations unless more stringent requirements are indicated or required by Project conditions to ensure satisfactory performance of dampproofing.
 - 1. Apply additional coats if recommended by manufacturer or required to achieve coverages indicated.
 - 2. Allow each coat of dampproofing to cure 24 hours before applying subsequent coats.
- B. Apply dampproofing to provide continuous plane of protection on exterior face of inner wythe of exterior masonry cavity walls.
 - 1. Lap dampproofing at least 1/4 inch onto flashing, masonry reinforcement, veneer ties, and other items that penetrate inner wythe.

2. Extend dampproofing over outer face of structural members and concrete slabs that interrupt inner wythe, and lap dampproofing at least 1/4 inch onto shelf angles supporting veneer.

3.4 COLD-APPLIED, CUT-BACK ASPHALT DAMPPROOFING

- A. On Exterior Face of Inner Wythe of Cavity Walls: Apply primer and one brush or spray coat at not less than 1 gal./100 sq. ft..

3.5 CLEANING

- A. Remove dampproofing materials from surfaces not intended to receive dampproofing.

END OF SECTION 071113